

EN206 Density Conformity - Variation report

08 March 2008




Table 13 - Heavyweight Concrete Density (QPA Guide)

Individual criterion = -130 kg + 100kg

Class limits / tolerance on target value = -100 kg + 100kg

Minimum number of results within class limits / tolerances per 20 consecutive non overlapping results = 18

Ref:- BS EN 12390-7: Testing hardened concrete - Part 7 Density of hardened concrete shall be to "water saturated" condition